

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>A61L 27/00, 29/00, 31/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/42147</b> <b>(43) International Publication Date:</b> 26 August 1999 (26.08.99)
<b>(21) International Application Number:</b> PCT/US99/03977 <b>(22) International Filing Date:</b> 23 February 1999 (23.02.99) <b>(30) Priority Data:</b> 60/075,523 23 February 1998 (23.02.98) US <b>(71) Applicant:</b> MASSACHUSETTS INSTITUTE OF TECHNOLOGY [US/US]; 77 Massachusetts Avenue, Cambridge, MA 02139 (US). <b>(72) Inventors:</b> LANGER, Robert, S.; 77 Lombard Street, Newton, MA 02158 (US). LENDLEIN, Andreas; Brgstrasse 35-37, D-52062 Aachen (DE). SCHMIDT, Annette; Semmelseisstrasse 17, D-52146 Wuerselen (DE). GRABLOWITZ, Hans; Blucherplatz 30, D-52068 Aachen (DE). <b>(74) Agent:</b> PABST, Patrea, L.; Arnall Golden & Gregory, LLP, 2800 One Atlantic Center, 1201 West Peachtree Street, Atlanta, GA 30309-3450 (US).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> BIODEGRADABLE SHAPE MEMORY POLYMERS  <b>(57) Abstract</b> <p>Biodegradable shape memory polymer compositions, articles of manufacture thereof, and methods of preparation and use thereof are described. In one embodiment the compositions include at least one hard segment and at least one soft segment. The <math>T_{trans}</math> of the hard segment is preferably between <math>-30</math> and <math>270</math> °C. At least one of the hard or soft segments can contain a cross-linkable group, and the segments can be linked by formation of an interpenetrating network or a semi-interpenetrating network, or by physical interactions of the segments. Objects can be formed into a given shape at a temperature above the <math>T_{trans}</math> of the hard segment, and cooled to a temperature below the <math>T_{trans}</math> of the soft segment. If the object is subsequently formed into a second shape, the object can return to its original shape by heating the object above the <math>T_{trans}</math> of the soft segment and below the <math>T_{trans}</math> of the hard segment.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## BIODEGRADABLE SHAPE MEMORY POLYMERS

### Background of the Invention

This application is generally in the area of shape memory polymers,  
5 and more particularly to biodegradable shape memory polymers.

Shape memory is the ability of a material to remember its original shape, either after mechanical deformation (Figure 1), which is a one-way effect, or by cooling and heating (Figure 2), which is a two-way effect. This phenomenon is based on a structural phase transformation.

10 The first materials known to have these properties were shape memory metal alloys (SMAs), including TiNi (Nitinol), CuZnAl, and FeNiAl alloys. The structure phase transformation of these materials is known as a martensitic transformation. These materials have been proposed for various uses, including vascular stents, medical guidewires, orthodontic  
15 wires, vibration dampers, pipe couplings, electrical connectors, thermostats, actuators, eyeglass frames, and brassiere underwires. These materials have not yet been widely used, in part because they are relatively expensive.

Shape memory polymers (SMPs) are being developed to replace or augment the use of SMAs, in part because the polymers are light, high in  
20 shape recovery ability, easy to manipulate, and economical as compared with SMAs. In the literature, SMPs are generally characterized as phase segregated linear block co-polymers having a hard segment and a soft segment. The hard segment is typically crystalline, with a defined melting point, and the soft segment is typically amorphous, with a defined glass  
25 transition temperature. In some embodiments, however, the hard segment is amorphous and has a glass transition temperature rather than a melting point. In other embodiments, the soft segment is crystalline and has a melting point rather than a glass transition temperature. The melting point or glass  
30 transition temperature of the soft segment is substantially less than the melting point or glass transition temperature of the hard segment.

When the SMP is heated above the melting point or glass transition temperature of the hard segment, the material can be shaped. This (original) shape can be memorized by cooling the SMP below the melting point or

glass transition temperature of the hard segment. When the shaped SMP is cooled below the melting point or glass transition temperature of the soft segment while the shape is deformed, a new (temporary) shape is fixed. The original shape is recovered by heating the material above the melting point or  
5 glass transition temperature of the soft segment but below the melting point or glass transition temperature of the hard segment. In another method for setting a temporary shape, the material is deformed at a temperature lower than the melting point or glass transition temperature of the soft segment, resulting in stress and strain being absorbed by the soft segment. When the  
10 material is heated above the melting point or glass transition temperature of the soft segment, but below the melting point (or glass transition temperature) of the hard segment, the stresses and strains are relieved and the material returns to its original shape. The recovery of the original shape, which is induced by an increase in temperature, is called the thermal shape  
15 memory effect. Properties that describe the shape memory capabilities of a material are the shape recovery of the original shape and the shape fixity of the temporary shape.

Several physical properties of SMPs other than the ability to memorize shape are significantly altered in response to external changes in  
20 temperature and stress, particularly at the melting point or glass transition temperature of the soft segment. These properties include the elastic modulus, hardness, flexibility, vapor permeability, damping, index of refraction, and dielectric constant. The elastic modulus (the ratio of the stress in a body to the corresponding strain) of an SMP can change by a  
25 factor of up to 200 when heated above the melting point or glass transition temperature of the soft segment. Also, the hardness of the material changes dramatically when the soft segment is at or above its melting point or glass transition temperature. When the material is heated to a temperature above the melting point or glass transition temperature of the soft segment, the  
30 damping ability can be up to five times higher than a conventional rubber product. The material can readily recover to its original molded shape following numerous thermal cycles, and can be heated above the melting

point of the hard segment and reshaped and cooled to fix a new original shape.

Conventional shape memory polymers generally are segmented polyurethanes and have hard segments that include aromatic moieties. U.S. Patent No. 5,145,935 to Hayashi, for example, discloses a shape memory polyurethane elastomer molded article formed from a polyurethane elastomer polymerized from of a difunctional diisocyanate, a difunctional polyol, and a difunctional chain extender.

Examples of polymers used to prepare hard and soft segments of known SMPs include various polyethers, polyacrylates, polyamides, polysiloxanes, polyurethanes, polyether amides, polyurethane/ureas, polyether esters, and urethane/butadiene copolymers. See, for example, U.S. Patent No. 5,506,300 to Ward et al.; U.S. Patent No. 5,145,935 to Hayashi; U.S. Patent No. 5,665,822 to Bitler et al.; and Gorden, "Applications of Shape Memory Polyurethanes," *Proceedings of the First International Conference on Shape Memory and Superelastic Technologies, SMST International Committee*, pp. 115-19 (1994).

Although these polymers have been proposed for a number of uses, their medical applications have been limited to devices which are not implanted or left in the body. It is desirable to have shape memory polymers, but which are biodegradable. Many other applications for biodegradable shape memory polymers are apparent, for example, for use in making diaper or medical drape linings, or in packagings for food or other materials where there are disposal problems. It is not apparent from the commercially available polyurethane materials that one could incorporate biodegradable materials into a shape memory polymer, and retain the structural and other physical and chemical properties which are essential to shape memory polymers and their application. Moreover, the components of the known polyurethane shape memory polymers contain aromatic groups which would be expected to not be biocompatible.

It is therefore an object of the present invention to provide biodegradable shape memory polymers.

It is still a further object of the present invention to provide shape memory polymers with physical and chemical properties and chemical structures that are different than those in conventional shape memory polymers.

5

### Summary of the Invention

Biodegradable shape memory polymer compositions, articles of manufacture thereof, and methods of preparation and use thereof are described. The polymer compositions include one or more hard segments and one or more soft segments, wherein the compositions are biocompatible and at least one of the segments is biodegradable or at least one of the segments is linked to another segment via a biodegradable linkage.

The melting point or glass transition temperature (hereinafter, the  $T_{trans}$ ) of the hard segment is at least 10 °C, and preferably 20 °C, higher than the  $T_{trans}$  of the soft segment. The  $T_{trans}$  of the hard segment is preferably between -30 and 270 °C, and more preferably between 30 and 150 °C. The ratio by weight of the hard segment:soft segments is between about 5:95 and 95:5, preferably between 20:80 and 80:20. The shape memory polymers contain at least one physical crosslink (physical interaction of the hard segment) or contain covalent crosslinks instead of a hard segment. The shape memory polymers can also be interpenetrating networks or a semi-interpenetrating networks.

In addition to changes in state from a solid to liquid state (melting point or glass transition temperature), hard and soft segments may undergo solid to solid state transitions, and can undergo ionic interactions involving polyelectrolyte segments or supramolecular effects based on highly organized hydrogen bonds.

Any polymers that are crystalline or amorphous and that have a  $T_{trans}$  within the range defined herein can be used to form the hard and soft segments. Representative biodegradable polymers include polyhydroxy acids, polyalkanoates, polyanhydrides, polyphosphazenes, polyetheresters, polyesteramides, polyesters, and polyorthoesters. Exemplary biodegradable linkages include ester, amide, anhydride, carbonate, and orthoester linkages.

Articles of manufacture can be prepared from the shape memory polymer compositions, for example, by injection molding, blowing, extrusion, and laser ablation. To prepare an object having a shape in memory, the object can be formed at a temperature above the  $T_{trans}$  of the hard segment, and cooled to a temperature below the  $T_{trans}$  of the soft segment. If the object subsequently is formed into a second shape, the object can be returned to its original shape by heating the object above the  $T_{trans}$  of the soft segment and below the  $T_{trans}$  of the hard segment.

Thermoset polymers can be prepared by pre-shaping macromonomers, for example, by extrusion, and fix-ing the original shape at a temperature above the  $T_{trans}$  of the thermoset polymer, for example, by photocuring reactive groups on the macromonomer.

#### Description of the Drawings

Figure 1 is an illustration of the one-way shape memory effect.

Figure 2 is an illustration of the two-way (thermal) shape memory effect.

Figure 3 is an illustration of combinations of suitable classes of thermoplastic materials.

Figure 4 is a diagram of a reaction sequence for the synthesis of a preferred photocrosslinker.

Figure 5 is an illustration of a photoinduced shape memory effect.

Figure 6 is an illustration of the mechanism of the thermal shape memory effect for a multiblock copolymer.

Figure 7 is a graph showing stress versus elongation for a multi-block copolymer shape memory polymer.

Figure 8 is a graph showing the melting temperature of diols, dimethacrylates, and thermosets of poly( $\epsilon$ -caprolactone) as a function of the molar mass weight  $M_n$  of the macromonomers.

### Detailed Description of the Invention

Biodegradable shape memory polymer compositions, articles of manufacture thereof, and methods of preparation and use thereof are described.

#### 5        Definitions

As used herein, the term "biodegradable" refers to materials that are bioresorbable and/or degrade and/or break down by mechanical degradation upon interaction with a physiological environment into components that are metabolizable or excretable, over a period of time from minutes to three  
10        years, preferably less than one year, while maintaining the requisite structural integrity. As used herein in reference to polymers, the term "degrade" refer to cleavage of the polymer chain, such that the molecular weight stays approximately constant at the oligomer level and particles of polymer remain following degradation. The term "completely degrade"  
15        refers to cleavage of the polymer at the molecular level such that there is essentially complete mass loss. The term "degrade" as used herein includes "completely degrade" unless otherwise indicated.

A polymer is a shape memory polymer if the original shape of the polymer is recovered by heating it above a shape recovering temperature  
20        (defined as the  $T_{trans}$  of a soft segment) even if the original molded shape of the polymer is destroyed mechanically at a lower temperature than the shape recovering temperature, or if the memorized shape is recoverable by application of another stimulus.

As used herein, the term "segment" refers to a block or sequence of  
25        polymer forming part of the shape memory polymer.

As used herein, the terms hard segment and soft segment are relative terms, relating to the  $T_{trans}$  of the segments. The hard segment(s) has a higher  $T_{trans}$  than the soft segment(s).

The shape memory polymers can include at least one hard segment  
30        and at least one soft segment, or can include at least one kind of soft segment wherein at least one kind of the soft segments are crosslinked, without the presence of a hard segment.



The hard segments can be linear oligomers or polymers, and can be cyclic compounds, such as crown ethers, cyclic di-, tri-, or oligopeptides, and cyclic oligo(ester amides).

5 The physical interaction between hard segments can be based on charge transfer complexes, hydrogen bonds, or other interactions, since some segments have melting temperatures that are higher than the degradation temperature. In these cases, there is no melting or glass transition temperature for the segment. A non-thermal mechanism, such as a solvent, is required to change the segment bonding.

10 The ratio by weight of the hard segment:soft segments is between about 5:95 and 95:5, preferably between 20:80 and 80:20.

#### Shape Memory Polymeric Compositions

Thermoplastic shape memory materials are shaped/molded to a desired shape above the  $T_{trans}$  of the hard segment(s) and cooled down to a temperature below the shape recovering temperature, where the polymer may  
15 undergo mechanical deformation and strains are generated in the polymer. The original shape of the deformed polymers are recovered by heating them to a temperature higher than their shape recovering temperature. Above this temperature, the strains in the polymer are relieved, allowing the polymer to return to its original shape. In contrast, thermoset shape memory materials  
20 are shaped/molded to a desired shape before the macromonomers used to form the thermoset polymers are polymerized. After the shape has been fixed, the macromonomers are polymerized.

The polymer compositions are preferably compressible by at least  
25 one percent or expandable by at least five one of the original thickness at a temperature below the shape recovering temperature, with the deformation being fixed by application of a stimulus such as heat, light, ultrasound, magnetic fields or electric fields. In some embodiments, the materials show a ratio of recovery of 98% (compare to experimental examples).

30 When significant stress is applied, resulting in an enforced mechanical deformation at a temperature lower than the shape recovering temperature, strains are retained in the soft segments or amorphous regions, and bulky shape change is kept even after the partial liberation of strain by

the elasticity of the polymer. If the configuration of the molecular chains is disturbed by influencing the regulated arrangement of molecular chains at a temperature lower than the glass transition temperature, rearrangement of the molecular chains is assumed to occur through the increase of the volume size and the decrease of the free volume content. The original shape is recovered by the contraction of the hard segment aggregates by the elevation of the temperature according to rigid control of chain conformations and the shape of the polymer is restored to the memorized shape.

In addition to changes in state from a solid to liquid state (melting point or glass transition temperature), hard or soft segments can undergo ionic interactions involving polyelectrolyte segments or supramolecular effects based on highly organized hydrogen bonds. The SM polymer can also undergo solid state to solid state transitions (e.g. change in morphology). Solid state to solid state transitions are well known to those of skill in the art, e.g. in poly(styrene-*block*-butadiene).

Various changes can take place to the structure of an object formed using the shape memory polymers. If the objects are three dimensional objects, the changes in shape can be two dimensional. If the objects are essentially two dimensional objects, such as fibers, then the changes in shape can be one dimensional, such as along the length. The thermal and electrical conductivity of the materials can also change in response to changes in temperature.

The moisture permeability of the compositions can be varied, especially when the polymer is formed into a thin film (i.e., less than about 10  $\mu\text{m}$ ). Some polymer compositions, in their original shape, have a sufficient permeability such that molecules of water vapor can be transmitted through the polymer film, while water molecules are not large enough to penetrate the polymer film. The resulting materials have low moisture permeability at temperatures below room temperature and high moisture permeability at temperatures above room temperature.

Stimuli other than temperature can be used to induce shape changes. As described with reference to certain embodiments below, the shape

changes can be elicited by exposure to light activation or an agent such as an ion which alters the interpolymer bonds.

### **I. Polymer Segments**

The segments preferably are oligomers. As used herein, the term  
5 "oligomer" refers to a linear chain molecule having a molecular weight up to 15,000 Da.

The polymers are selected based on the desired glass transition  
temperature(s) (if at least one segment is amorphous) or the melting point(s)  
(if at least one segment is crystalline), which in turn is based on the desired  
10 applications, taking into consideration the environment of use. Preferably,  
the number average molecular weight of the polymer block is greater than  
400, and is preferably in the range of between 500 and 15,000.

The transition temperature at which the polymer abruptly becomes  
soft and deforms can be controlled by changing the monomer composition  
15 and the kind of monomer, which enables one to adjust the shape memory  
effect at a desired temperature.

The thermal properties of the polymers can be detected, for example,  
by dynamic mechanical thermoanalysis or differential scanning calorimetry  
(DSC) studies. In addition the melting point can be determined using a  
20 standard melting point apparatus.

#### **1. Thermoset or thermoplastic polymers.**

The polymers can be thermoset or thermoplastic polymers, although  
thermoplastic polymers may be preferred due to their ease of molding.

Preferably, the degree of crystallinity of the polymer or polymeric  
25 block(s) is between 3 and 80%, more preferably between 3 and 60%. When  
the degree of crystallinity is greater than 80% while all soft segments are  
amorphous, the resulting polymer composition has poor shape memory  
characteristics.

The tensile modulus of the polymers below the  $T_{trans}$  is typically  
30 between 50 MPa and 2 GPa (gigapascals), whereas the tensile modulus of the  
polymers above the  $T_{trans}$  is typically between 1 and 500 MPa. Preferably,  
the ratio of elastic modulus above and below the  $T_{trans}$  is 20 or more. The

higher the ratio, the better the shape memory of the resulting polymer composition.

The polymer segments can be natural or synthetic, although synthetic polymers are preferred. The polymer segments can be biodegradable or non-  
5 biodegradable, although the resulting SMP composition is biodegradable biocompatible polymers are particularly preferred for medical applications. In general, these materials degrade by hydrolysis, by exposure to water or enzymes under physiological conditions, by surface erosion, bulk erosion, or a combination thereof. Non-biodegradable polymers used for medical  
10 applications preferably do not include aromatic groups, other than those present in naturally occurring amino acids.

Representative natural polymer segments or polymers include proteins such as zein, modified zein, casein, gelatin, gluten, serum albumin, and collagen, and polysaccharides such as alginate, celluloses, dextrans,  
15 pullulane, and polyhyaluronic acid, as well as chitin, poly(3-hydroxyalkanoate)s, especially poly( $\beta$ -hydroxybutyrate), poly(3-hydroxyoctanoate) and poly(3-hydroxyfatty acids).

Representative natural biodegradable polymer segments or polymers include polysaccharides such as alginate, dextran, cellulose, collagen, and  
20 chemical derivatives thereof (substitutions, additions of chemical groups, for example, alkyl, alkylene, hydroxylations, oxidations, and other modifications routinely made by those skilled in the art), and proteins such as albumin, zein and copolymers and blends thereof, alone or in combination with synthetic polymers.

25 Representative synthetic polymer blocks include polyphosphazenes, poly(vinyl alcohols), polyamides, polyester amides, poly(amino acid)s, synthetic poly(amino acids), polyanhydrides, polycarbonates, polyacrylates, polyalkylenes, polyacrylamides, polyalkylene glycols, polyalkylene oxides, polyalkylene terephthalates, polyortho esters, polyvinyl ethers, polyvinyl  
30 esters, polyvinyl halides, polyvinylpyrrolidone, polyesters, polylactides, polyglycolides, polysiloxanes, polyurethanes and copolymers thereof.

Examples of suitable polyacrylates include poly(methyl methacrylate), poly(ethyl methacrylate), poly(butyl methacrylate),

poly(isobutyl methacrylate), poly(hexyl methacrylate), poly(isodecyl methacrylate), poly(lauryl methacrylate), poly(phenyl methacrylate), poly(methyl acrylate), poly(isopropyl acrylate), poly(isobutyl acrylate) and poly(octadecyl acrylate).

5           Synthetically modified natural polymers include cellulose derivatives such as alkyl celluloses, hydroxyalkyl celluloses, cellulose ethers, cellulose esters, nitrocelluloses, and chitosan. Examples of suitable cellulose derivatives include methyl cellulose, ethyl cellulose, hydroxypropyl cellulose, hydroxypropyl methyl cellulose, hydroxybutyl methyl cellulose,  
10 cellulose acetate, cellulose propionate, cellulose acetate butyrate, cellulose acetate phthalate, carboxymethyl cellulose, cellulose triacetate and cellulose sulfate sodium salt. These are collectively referred to herein as "celluloses".

Representative synthetic degradable polymer segments or polymers include polyhydroxy acids, such as polylactides, polyglycolides and  
15 copolymers thereof; poly(ethylene terephthalate); poly(hydroxybutyric acid); poly(hydroxyvaleric acid); poly[lactide-co-( $\epsilon$ -caprolactone)]; poly[glycolide-co-( $\epsilon$ -caprolactone)]; polycarbonates, poly(pseudo amino acids); poly(amino acids); poly(hydroxyalkanoate)s; polyanhydrides; polyortho esters; and blends and copolymers thereof.

20           Examples of non-biodegradable polymer segments or polymers include ethylene vinyl acetate, poly(meth)acrylic acid, polyamides, polyethylene, polypropylene, polystyrene, polyvinyl chloride, polyvinylphenol, and copolymers and mixtures thereof.

Rapidly bioerodible polymers such as poly(lactide-co-glycolide)s,  
25 polyanhydrides, and polyorthoesters, which have carboxylic groups exposed on the external surface as the smooth surface of the polymer erodes, also can be used. In addition, polymers containing labile bonds, such as polyanhydrides and polyesters, are well known for their hydrolytic reactivity. Their hydrolytic degradation rates can generally be altered by simple  
30 changes in the polymer backbone and their sequence structure.

Various polymers, such as polyacetylene and polypyrrole, are conducting polymers. These materials are particularly preferred for uses in which electrical conductance is important. Examples of these uses include

tissue engineering and any biomedical application where cell growth is to be stimulated. These materials may find particular utility in the field of computer science, as they are able to absorb heat without increasing in temperature better than SMAs. Conducting shape memory polymers are  
5 useful in the field of tissue engineering to stimulate the growth of tissue, for example, nerve tissue.

## 2. Hydrogels.

The polymer may be in the form of a hydrogel (typically absorbing up to about 90% by weight of water), and can optionally be ionically  
10 crosslinked with multivalent ions or polymers. Ionic crosslinking between soft segments can be used to hold a structure, which, when deformed, can be reformed by breaking the ionic crosslinks between the soft segments. The polymer may also be in the form of a gel in solvents other than water or aqueous solutions. In these polymers, the temporary shape can be fixed by  
15 hydrophilic interactions between soft segments.

Hydrogels can be formed from polyethylene glycol, polyethylene oxide, polyvinyl alcohol, polyvinyl pyrrolidone, polyacrylates, poly (ethylene terephthalate), poly(vinyl acetate), and copolymers and blends thereof. Several polymeric segments, for example, acrylic acid, are  
20 elastomeric only when the polymer is hydrated and hydrogels are formed. Other polymeric segments, for example, methacrylic acid, are crystalline and capable of melting even when the polymers are not hydrated. Either type of polymeric block can be used, depending on the desired application and conditions of use.

25 For example, shape memory is observed for acrylic acid copolymers only in the hydrogel state, because the acrylic acid units are substantially hydrated and behave like a soft elastomer with a very low glass transition temperature. The dry polymers are not shape memory polymers. When dry, the acrylic acid units behave as a hard plastic even above the glass transition  
30 temperature and show no abrupt change in mechanical properties on heating. In contrast, copolymers including methyl acrylate polymeric segments as the soft segments show shape memory properties even when dry.

### 3. Polymers Capable of Forming a Gel at Increased Temperatures.

Certain polymers, for example, poly(ethylene oxide-co-propylene oxide) (PLURONICS<sup>TM</sup>), are soluble in water at temperatures lower than  
5 body temperature and become hydrogels at temperatures higher than body temperature. Incorporation of these polymers as segments in shape memory polymers provides them with the ability to response to changes in temperature in a manner opposite that of typical shape memory polymers. These materials recover their shape when cooled below their shape recovery  
10 temperature, rather than being heated above their shape recovery temperature. This effect is called inversed thermal shape memory effect. Shape memory polymer compositions including these polymer segments are useful in various biomedical applications where the polymer can be inserted as a liquid, and cooled to recover an intended shape *in situ*. The inverse  
15 thermal shape memory effect can be obtained by incorporating two different segments into a polymer that are miscible at temperatures lower than  $T_{misc}$ , but are immiscible at higher temperatures. The phase separation at higher temperatures stabilizes the temporary shape.

The polymers can be obtained from commercial sources such as  
20 Sigma Chemical Co., St. Louis, MO.; Polysciences, Warrenton, PA; Aldrich Chemical Co., Milwaukee, WI; Fluka, Ronkonkoma, NY; and BioRad, Richmond, CA. Alternately, the polymers can be synthesized from monomers obtained from commercial sources, using standard techniques.

## II. Assembly of Polymer Segments

25 The shape memory polymer include one or more hard segments and one or more soft segments, wherein at least one of the segments is biodegradable or at least one of the segments is linked to another segment via a biodegradable linkage. Representative biodegradable linkages include  
ester-, amide-, anhydride-, carbonate-, or orthoester linkages.

### 30 1. Polymer Structures.

The shape memory effect is based on the polymer morphology. With respect to thermoplastic elastomers, the original shape of an object is fixed by physical crosslinks caused by the hard segment. With respect to

thermoset polymers, the soft segments are covalently crosslinked instead of having hard segments. The original shape is set by the crosslinking process.

In contrast to prior art segmented polyurethane SMPs, the segments of the compositions described herein need not be linear. The segments can  
5 be partially grafted or attached in dendremeric side groups.

*A. Thermoplastic and Thermoelastic Polymers*

The polymers can be in the form of linear diblock-, triblock-, tetrablock, or multiblock copolymers, branch or graft polymers, thermoplastic elastomers, which contain dendritic structures, and blends  
10 thereof. Figure 3 illustrates some of the combinations of suitable classes of thermoplastic materials forming the hard and soft segments. The thermoplastic shape memory polymer composition also can be a blend of one or more homo- or co-polymer with one or more diblock-, triblock-, tetrablock, or multiblock copolymers, branch or graft polymers. These types  
15 of polymers are well known to those of skill in the art.

As used herein, the term "degradable thermoset" refers to (i) thermosets SMPs containing only one soft segment, which contains cleavable bonds, and (ii) thermosets containing more than one soft segment, wherein at least one soft segment is degradable or wherein the different soft  
20 segments are connected by cleavable bonds. There are four different types of thermoset polymers that have shape memory capability. These include polymer networks, semi-interpenetrating networks, interpenetrating networks, and mixed-interpenetrating networks.

*i. Polymer Networks*

A polymer network is prepared by covalently crosslinking  
25 macromonomers, i.e., polymers which contain polymerizable endgroups such as carbon-carbon double bonds. The polymerization process can be induced by using light or heat sensitive initiators or by curing with ultraviolet light ("UV-light") without an initiator. Shape memory polymer networks are  
30 prepared by crosslinking one or more soft segments which correspond to one or more thermal transitions.

In an embodiment preferred for biomedical applications, the crosslinking is performed using a photocrosslinker and requires no chemical



initiator. The photocrosslinker advantageously eliminates the need for initiator molecules, which may be toxic. Figure 4 is a diagram of a reaction sequence for the synthesis of a preferred photocrosslinker, which produces an overall yield of about 65%.

5 *ii. Interpenetrating Networks*

Interpenetrating networks ("IPN") are defined as networks where two components are crosslinked, but not to each other. The original shape is determined by the network with the highest crosslink density and the highest mechanical strength. The material has at least two  $T_{trans}$  corresponding to the different soft segments of both networks.

### iii. Mixed Interpenetrating Network

A mixed IPN includes at least one physically crosslinked polymer network (a thermoplastic polymer) and at least one covalently crosslinked polymer network (a thermoset polymer) that cannot be separated by any physical methods. The original shape is set by the covalently crosslinked network. The temporary shapes correspond to the  $T_{trans}$  of the soft segments and the  $T_{trans}$  of the hard segment of the thermoplastic elastomer component.

A particularly preferred mixed interpenetrating network is prepared by polymerizing a reactive macromonomer in the presence of a thermoplastic polymer, for example, by the photopolymerization of carbon-carbon double bonds. In this embodiment, the ratio by weight of thermoset polymer to thermoplastic polymer is preferably between 5:95 and 95:5, more preferably, between 20:80 and 80:20.

#### iv. Semi-Interpenetrating Networks

25                Semi-interpenetrating networks ("semi-IPN") are defined as two independent components, where one component is a crosslinked polymer (a polymer network) and the other component is a non-crosslinked polymer (a homopolymer or copolymer), wherein the components cannot be separated by physical methods. The semi-IPN has at least one thermal transition

30                corresponding to the soft segment(s) and the homo- or co-polymer components. The crosslinked polymer preferably constitutes between about 10 and 90% by weight of the semi-interpenetrating network composition.

*v. Polymer Blends*

In a preferred embodiment, the shape memory polymer compositions described herein are formed of a biodegradable polymer blend. As used herein, a "biodegradable polymer blend" is a blend having at least one  
5 biodegradable polymer.

The shape memory polymers can exist as physical mixtures of thermoplastic polymers. In one embodiment, a shape memory polymer composition can be prepared by interacting or blending two thermoplastic polymers. The polymers can be semicrystalline homopolymers,  
10 semicrystalline copolymers, thermoplastic elastomers with linear chains, thermoplastic elastomers with side chains or any kind of dendritic structural elements, and branched copolymers, and these can be blended in any combination thereof.

For example, a multiblock copolymer with a hard segment with a  
15 relatively high  $T_{trans}$  and a soft segment with a relatively low  $T_{trans}$  can be mixed or blended with a second multiblock copolymer with a hard segment with a relatively low  $T_{trans}$  and the same soft segment as that in the first multiblock copolymer. The soft segments in both multiblock copolymers are identical, so the polymers are miscible in each other when the soft segments  
20 are melted. There are three transition temperatures in the resulting blend - that of the first hard segment, that of the second hard segment, and that of the soft segment. Accordingly, these materials are able to memorize two different shapes. The mechanical properties of these polymers can be adjusted by the changing the weight ratio of the two polymers.

25 Other kinds of blends of at least two multiblock copolymers, in which at least one of the segments is miscible with at least one of the segments of the other multiblock copolymers, can be prepared. If two different segments are miscible and build one domain together, then the thermal transition of this domain depends on the weight content of the two segments. The  
30 maximum number of memorized shapes results from the number of thermal transitions of the blend.

Shape memory blends may have better shape memory capabilities than the blend components alone. Shape memory blends are composed of at

least one multiblock copolymer and at least one homo- or copolymer. In principle di-, tri, tetra-block copolymers can be used instead of a multiblock copolymer.

Shape memory blends are highly useful in industrial applications, since a broad range of mechanical, thermal, and shape memory capabilities can be obtained from only two or three basic polymers by blending them in different weight ratios. A twin screw extruder is an example of standard process equipment that could be used to mix the components and process the blend.

### 10 **III. Methods of Making the SMPs**

The polymers described above are either commercially available or can be synthesized using routine chemistry. Those of skill in the art can readily prepare the polymers using known chemistry. Examples 1 and 2 below describe experimental procedures used to prepare the SMPs.

### 15 **IV. Methods of Shaping the SMP Compositions**

The compositions can be formed into a first shape under appropriate conditions, for example, at a temperature above the  $T_{trans}$  of the hard segments, and allowed to cool below the  $T_{trans}$  of the soft segment(s). Standard techniques are extrusion and injection molding. Optionally, the object can be re-formed into a second shape. Upon application of heat or other appropriate set of conditions, the object returns to original shape.

Thermoset polymers can be prepared by extruding the pre-polymerized material (macromonomers), and fixing the original shape at a temperature above the  $T_{trans}$  of the thermoset polymer, for example, by photocuring reactive groups on the monomer. The temporary shape is fixed by cooling the material below  $T_{trans}$  after deforming the material. Figure 5 illustrates a photoinduced shape memory effect.

The crosslinking also can be performed in a solution of the macromonomers. The solvent is removed from the formed gel in a subsequent step.

Those compositions formed of thermoplastic polymers can be blown, extruded into sheets or shaped by injection molding, for example, to form fibers. The compositions can also be shaped by other methods known to

those of skill in the art for shaping solid objects, for example, laser ablation, micromachining, use of a hot wire, and by CAD/CAM (computer aided design/computer aided manufacture) processes. These processes are preferred for shaping thermoset polymers.

5     **V. Therapeutic, Prophylactic, and Diagnostic Applications**

Any of a variety of therapeutic, prophylactic and/or diagnostic agents can be incorporated within the polymer compositions, which can locally or systemically deliver the incorporated agents following administration to a patient.

10     **1. Therapeutic, Diagnostic and Prophylactic Applications**

Any of a variety of therapeutic agents can be incorporated within the particles, for local or systemic delivery of the incorporated agents following administration to a patient. Examples include synthetic inorganic and organic compounds or molecules, proteins and peptides, polysaccharides and  
15     other sugars, lipids, and nucleic acid molecules having therapeutic, prophylactic or diagnostic activities. Nucleic acid molecules include genes, plasmid DNA, naked DNA, antisense molecules which bind to complementary DNA to inhibit transcription, ribozymes and ribozyme guide sequences. The agents to be incorporated can have a variety of biological  
20     activities, such as vasoactive agents, neuroactive agents, hormones, growth factors, cytokines, anaesthetics, steroids, anticoagulants, anti-inflammatories, immunomodulating agents, cytotoxic agents, prophylactic agents, antibiotics, antivirals, antisense, antigens, and antibodies. In some instances, the proteins may be antibodies or antigens which otherwise would have to be  
25     administered by injection to elicit an appropriate response. Proteins are defined as consisting of 100 amino acid residues or more; peptides are less than 100 amino acid residues. Unless otherwise stated, the term protein refers to both proteins and peptides. Polysaccharides, such as heparin, can also be administered. Compounds with a wide range of molecular weight,  
30     for example, between 10 and 500,000 grams per mole, can be encapsulated.

Imaging agents which may be utilized include commercially available agents used in positron emission tomography (PET), computer assisted tomography (CAT), single photon emission computerized

tomography, x-ray, fluoroscopy, magnetic resonance imaging (MRI), and ultrasound agents.

## **VI. Articles, Devices and Coatings**

5       The SMP compositions can be used to prepare numerous articles of manufacture, for use in biomedical and other applications.

### **1. Articles and Devices for Biomedical Applications**

10       The polymer compositions can be used to prepare articles of manufacture for use in biomedical applications. For example, sutures, orthodontic materials, bone screws, nails, plates, catheters, tubes, films, stents, orthopedic braces, splints, tape for preparing casts, and scaffolds for tissue engineering, contact lenses, drug delivery devices, implants, and thermal indicators, can be prepared.

15       The SMP compositions are preferably prepared from biocompatible polymers, and, for most applications, from biodegradable polymers. Biodegradable polymers degrade at a controlled rate depending on the composition and crosslinking of the polymer. Degradable polymeric implants eliminate the need for implant retrieval and can be used simultaneously to deliver therapeutic agents.

20       The materials can be used in many applications requiring load-bearing capacities and controlled degradation.

      The polymer compositions can be formed into the shape of an implant which can be implanted within the body to serve a mechanical function. Examples of such implants include rods, pins, screws, plates and anatomical shapes.

25       A particularly preferred use of the compositions is to prepare sutures that have a rigid enough composition to provide for ease of insertion, but upon attaining body temperature, soften and form a second shape that is more comfortable for the patient while still allowing healing.

30       Another preferred use is in the area of catheters. A catheter can be rigid at body temperature for ease of insertion, but, after warming to body temperature, can soften to provide comfort to the patient.

      The polymer compositions can be combined with fillers, reinforcement materials, radioimaging materials, excipients or other

materials as needed for a particular implant application. Examples of fillers include calcium-sodium-metaphosphate which is described in U.S. Patent No. 5,108,755. Those of skill in the art can readily determine a suitable amount of these materials to include in the compositions.

5           The articles can incorporate various therapeutic and/or diagnostic agents, as described above.

## 2. Non-Medical Applications

There are numerous applications for the shape memory polymer compositions other than biomedical applications.

10           Examples of non-medical type applications for biodegradable polymers include items for which disposal is an issue, such as disposable diapers and packaging materials.

## 3. Coatings with controlled degradation

Shape memory polymers can be designed so that the degradation rate is varied. For example, in one embodiment, a hydrolytically degradable polymer can be selectively protected by applying a hydrophobic SMP coating that temporarily prevents water from reaching the hydrolytically cleavable bonds of the bulk polymer. The protective feature of the coating then can be modified when desired by applying an external stimulus such that the diffusion properties of coating are altered to permit water or other aqueous solutions to permeate through the coating and initiate the degradation process. If the hydrolysis rate is relatively high compared to the diffusion rate of water, then the diffusion rate of water through the coating determines the degradation rate. In another embodiment, a hydrophobic coating consisting of densely crosslinked soft segments can be used as a diffusion barrier for water or aqueous solutions. The soft segments should be at least partially crosslinked by linkages that can be cleaved by application of a stimulus. The diffusion rate of water can be increased by lowering the crosslinking density.

## 30   **VII. Methods of Use**

Certain articles of manufacture are designed to hold their intended shape unless acted upon in a manner inconsistent with their normal use. For example, a car bumper will hold its intended shape unless it has been

impacted. These articles of manufacture are to be used in their intended shape and repaired, for example, by application of heat, once they are damaged.

Other articles of manufacture are designed to be used such that the first shape is intended for an initial use, and a second shape is intended for a subsequent use. Examples of these include biomedical devices which can form a second shape upon reaching at body temperature, or upon application of an external stimulus which heats the device above body temperature.

Still other articles of manufacture are designed to be used such that their shape changes in reaction to, or adjustment to, changes in temperature, such as thermosensors in medical devices.

The present invention will be further understood with reference to the following non-limiting examples.

#### **Example 1: Copolyesterurethane Shape Memory Polymers**

A group of biocompatible and biodegradable multiblock-copolymers showing a thermal shape memory effect was synthesized. These polymers were composed of a crystallizable hard segment ( $T_m$ ) and a soft segment having a thermal transition temperature  $T_{trans}$  between room and body temperature. In contrast to the prior art segmented polyurethanes, the hard segment was an oligoester or an oligoetherester and did not contain any aromatic component.

The mechanism for programming the temporary shape and recovering the permanent shape of a multiblock-copolymer is shown in Figure 6. The permanent shape of the materials was set by melting the polymer and cooling above  $T_{trans}$  (Fig. 6 – top pos.). Then, the polymer was formed into its temporary shape (Fig. 6 – right pos.), which was fixed by cooling below  $T_{trans}$  (Fig. 6 – bottom pos.). After unloading, the permanent shape was recovered by reheating above  $T_{trans}$ .

Synthesis of Telechelics, oligomers with functional groups at both ends.

The telechelic macrodiol were synthesized by ring opening polymerization of cyclic monomers with di(n-butyl)tin oxide as a transesterification catalyst under a  $N_2$  atmosphere.

#### **Hard Segment**

$\alpha,\omega$ -dihydroxy [oligo(ethylene glycol glycolate) ethylene oligo (ethylene glycol glycolate)] - (PDS1200 and PDS1300) was prepared as follows. The monomer p-dioxane-2-one was obtained by distillation (thermal depolymerization) of the oligomer prior to use. 57 g (0.63 mol) of the monomer, 0.673 g (10.9 mmol) ethylene glycol, and 0.192 g (0.773 mmol) di(n-butyl) tin oxide were heated to 80 °C for 24 h. The end of the reaction (equilibrium) was determined by GPC. The product was soluted in hot 1,2-dichloroethane and filtered hot through a Buechner-funnel filled with silica gel. The product was obtained by precipitation in hexanes and dried in vacuo for 6 h.

### Soft Segment

#### *i. Crystalline*

Poly( $\epsilon$ -caprolactone)-diols with different  $M_n$  are commercially available, for example, from Aldrich and Polysciences. PCL-2000 was used herein.

#### *ii. Amorphous*

$\alpha,\omega$ -dihydroxy [oligo(L-lactate-co-glycolate) ethylene oligo (L-lactate-co-glycolate)] - (abbr.: PLGA2000-15) was prepared as follows. In a 1000 ml two-neck round bottomed flask, 300 g (2.08 mol) of L,L-dilactide, 45 g (0.34 mol) of diglycolide and 4.94 g (0.80 mol) ethylene glycol were heated to melt at 40 °C and stirred. 0.614 g (2.5 mmol) di(n-butyl) tin oxide was added. After 7 h, the reaction reached equilibrium as determined by GPC. The reaction mixture was soluted in 1,2-dichloroethane and purified in a silica gel column. The product was obtained by precipitation in hexanes and dried *in vacuo* for 6 h.

### Properties of Telechelics

The molecular weight  $M_n$  and thermal properties of the macrodiols were determined as shown in Table 1 below.

**Table 1: Molecular Weight and Thermal Properties of the Macrodiols**

Label	$M_n$ GPC [g·mol <sup>-1</sup> ]	$M_n$ VPO [g·mol <sup>-1</sup> ]	$T_m$ [°C]	$\Delta H$ [J·g <sup>-1</sup> ]	$T_g$ [°C]	$\Delta C_p$ [J·g <sup>-1</sup> ]
PCL2000	1980	1690	43	73.5	<-40	-
PDS1300	1540	1340	97	74.5	<-20	-
PDS1200	2880	1230	95	75.0	<-20	-



PLGA2000	2020	1960	-	-	29.0	0.62
----------	------	------	---	---	------	------

### Synthesis of Thermoplastic Elastomers (Multiblock Copolymer)

In a 100 ml two-neck round-bottomed flask connected to a soxleth extractor filled with molecular sieve 0.4 nm, two different macrodiols (one  
 5 hard segment and one soft segment) as described in Table 2 below were soluted in 80 ml 1,2-dichloroethane. The mixture was refluxed to dry by azeotropic extraction of the solvent. Freshly distilled trimethylhexane-1,6-diisocyanate was added with a syringe, and the reaction mixture was heated to 80 °C for at least 10 days. At regular intervals, samples of the mixture  
 10 were taken to determine the molecular weight of the polymer by GPC. At the end of the reaction, the product was obtained by precipitating the polymer in hexanes and purified by repeatedly dissolving in 1,2-dichloroethane and precipitating in hexanes.

Multiblock copolymers were prepared from the following two types  
 15 of polymers.

(i) PDC polymers contain poly( $\epsilon$ -caprolactone).  $T_{trans}$  for the soft segment is the melting point.

(ii) PDL polymers contain a  $\alpha,\omega$ -dihydroxy [oligo(*L*-lactate-co-glycolate) ethylene oligo (*L*-lactate-co-glycolate)].  $T_{trans}$  for the soft segment  
 20 is the glass transition point.

**Table 2: Synthesis of Multiblock Copolymers**

Polymer	1. Diol	m [g]	n [mmol]	2. Diol	m [g]	n [mmol]	TMDI [mmol]	time [d]
PDC22	PDS1200	3,0245	2,653	PCL2k	6,0485	3,024	5,738	10
PDL23	PDS1200	2,2787	2,000	PLGA2k	6.1443	3,070	5,163	10
PDC27	PDS1300	2,5859	1,724	PCL2k	5,3611	2,681	4,368	14
PDC40	PDS1300	3,6502	2,433	PCL2k	3,9147	1,957	4,510	13
PDC31	PDS1300	3,2906	2,194	PCL2k	4,8619	2,431	4,500	16
PDL30	PDS1300	3,7115	2,474	PLGA2k	4,0205	2,011	4,480	16

### Properties of the Thermoplastic Elastomers

The physical, mechanical, and degradation properties determined for the  
 25 compositions are provided in Tables 3-9 below.

The hydrolytic degradation behavior of the new materials were tested in buffer solution pH 7 at 37 °C. It was shown that the polymers are

completely degradable and their degradation rate can be adjusted by the concentration of easily hydrolysable ester bonds. The values for loss of relative mass  $m_r = m(t_0)/m(t)$  in % at 37 °C, and, loss of relative molecular weight  $M_r = M_w(t)/M_w(t_0)$  in % at 37°C:

- 5           The toxicity of two different multiblock-copolymers was investigated using a chicken egg test. It was shown that blood vessels developed regularly and their condition was not influenced by the polymer samples.

**Table 3: Composition of the Copolyester Urethanes  
Determined by 400 MHz <sup>1</sup>H-NMR-Spectroscopy**

Label	Hard Segment	Weight Content [%]*	Soft Segment	Weight Content [%]*
PDL23	PDS	23.0	PLGA	54.2
PDL30	PDS	30.0	PLGA	52.1
PDC22	PDS	22.0	PCL	64.5
PDC27	PDS	27.0	PCL	61.1
PDC31	PDS	31.1	PCL	55.4
PDC40	PDS	40.4	PCL	46.2

- 10       \* The difference to 100% is the urethane content.

**Table 4: Molecular Weight  $M_w$  of the Copolyester Urethanes Films  
Determined by Multidetector-GPC**

Label	Polymer Film		
	$M_w( LS )$ [g·mol <sup>-1</sup> ]	$M_w( Visc )$ [g·mol <sup>-1</sup> ]	dn/dc [ml·g <sup>-1</sup> ]
PDL23	161,500	149,000	0.065
PDL30	79,100	83,600	0.057
PDC22	119,900	78,500	0.078
PDC27	72,700	61,100	0.080
PDC31	110,600	108,600	0.065
PDC40	93,200	86,300	0.084

- 15       **Table 5: Transition Temperatures  $T_m$  and  $T_g$ , Enthalpies of Fusion  $\Delta H_m$   
and Change in Heat Capacity  $\Delta C_p$  of the Polymer Films from  
DSC**

Measurements (Values Given from Second Heating Process)

Label	$T_{m1}$ [°C]	$\Delta H_{m1}$ [J·g <sup>-1</sup> ]	$T_g$ [°C]	$\Delta C_p$ [J·g <sup>-1</sup> ]	$T_{m2}$ [°C]	$\Delta H_{m2}$ [J·g <sup>-1</sup> ]
PDL23	-	-	34.5	0.38	-	-
PDL30	-	-	33.5	0.25	85.0	8.5
PDC22	35.0	26.0	-	-	-	-
PDC27	37.0	25.0	-	-	75,5	3.5
PDC31	36.5	28.5	-	-	76,5	5.5
PDC40	35.0	7.0	-	-	77,5	7.0

**Table 6: Mechanical Properties of Polymer Films  
at 50 °C from Tensile Tests**

Code	E-Modulus [MPa]	$\epsilon_r$ [%]	$\sigma_r$ [MPa]	$\epsilon_{max}$ [%]	$\sigma_{max}$ [MPa]
PDC27	1.5	1,350	2.1	1,300	2.3
PDC31	1.5	1,400	4.9	1,300	5.4
PDC40	4.0	1,250	5.8	1,300	5.9
PDL30	2.0	1,400	2.1	1,250	2.3

5 **Table 7: PDL22 Degradability**

Degradation Time [d]	$M_r$ (viscosimetry) [%]	$M_r$ (light scattering) [%]
14	81.3	85.7
21	67.1	74.6
29	62.9	65.6
42	43.6	47.7
56	54.4	41.9

**Table 8: PDL23 Degradability**

Degradation Time [d]	$M_r$ (viscosimetry) [%]	$M_r$ (light scattering) [%]
14	61.1	87.3
21	40.7	76.7
29	32.8	62.2
42	17.4	46.7
56	16.9	18.5

**Table 9: Loss of Relative Mass**

	PDC22	PDL23
Degradation Time [%]	$m_r$ [%]	$m_r$ [%]
14	99.2	98.1
21	99.3	97.5
29	98.6	97.2
42	98.3	96.9
56	97.3	93.3

10

### Shape Memory Properties

Figure 7 shows the results of tensile tests performed on the multiblock copolymers, as a function of the number of thermolytic cycles.

The average shape fixity rate of thermocyclicly treated polymers and the

15 dependency of strain recovery rates as a function of the number of cycles is

shown below in Tables 10 and 11, respectively. The polymers have a high shape fixity, and an equilibrium state was achieved after only two cycles.

**Table 10: Average Shape Fixity Rate  $R_f$**

Label	$R_f$
	[%]
PDC27	97.9
PDC40	96.2
PDL30	97.7

5 **Table 11: Cycle Number Dependence of Strain Recovery Rates  $R_r$**

	PDC27	PDC40	PDL23
Number of Cycles	$R_r$	$R_r$	$R_r$
	[%]	[%]	[%]
2	77.3	73.7	93.8
3	93.2	96.3	98.8
4	98.5	98.7	98.9
5	98.5	98.7	98.8

**Example 2: Degradable Shape Memory Thermoset  
With Crystallizable Soft Segment**

10 A range of poly( $\epsilon$ -caprolactone) dimethacrylates and thermosets were evaluated for their mechanical and shape memory properties.

Synthesis of Macromonomer

Poly( $\epsilon$ -caprolactone) dimethacrylates (PCLDMAs) were prepared as follows. To a solution of poly( $\epsilon$ -caprolactone) diol with  $M_n = 2'000 \text{ gmol}^{-1}$  (20.0 g, 10 mmol) and triethylamine (5.3 mL, 38 mmol) in 200 mL of dry  
15 THF, methacryloyl chloride (3.7 mL, 38 mmol) was added dropwise at 0 °C. The solution was stirred at 0 °C for 3 days and precipitated salt filtered off. After concentrating the mixture at room temperature under reduced pressure, 200 mL of ethyl acetate was added, and the solution filtered again and precipitated into a ten-fold excess of a mixture of hexanes, ethyl ether, and  
20 methanol (18:1:1). The colorless precipitate was collected, soluted in 200 mL of dichloroethane, precipitated again, and dried carefully at room temperature at reduced pressure.

Synthesis of Thermosets

25 The macromonomer (or the monomer mixture) was heated to 10 °C above its melting temperature ( $T_m$ ) and filled into a mould formed by two

glass plates (25 mm x 75 mm) and a teflon spacer of 0.60 mm thickness. To achieve a good homogeneity, the mould was stored at  $T_m$  for another hour. Photocuring was performed on a heated plate at  $T_m$  for 15 min. The distance between heat lamp head and sample was 5.0 cm. After cooling to room temperature, the sample was extracted and swollen with a 100-fold excess of dichloromethane overnight and washed carefully. Finally, the sample was dried at room temperature under reduced pressure.

#### Properties of Macromonomers and Thermosets

Table 12 below lists the poly( $\epsilon$ -caprolactone) dimethacrylates that were prepared, along with the respective degree of acrylation ( $D_a$ ) (%). The number following PCLDMA is the molecular weight  $M_n$  of the poly( $\epsilon$ -caprolactone) diol used in the synthesis as determined using  $^1\text{H-NMR}$  and GPC, rounded to 500.

**Table 12: Poly( $\epsilon$ -caprolactone) Diol and Degree of Acrylation**

Name	$D_a$ [%]
PCLDMA1500	87
PCLDMA2000	92
PCLDMA3500	96
PCLDMA4500	87
PCLDMA6500	93
PCLDMA7000	85
PCLDMA10000	86

Figure 8 shows the melting temperature ( $T_m$ ) of diols, dimethacrylates, and thermosets of poly( $\epsilon$ -caprolactone) as a function of the molar mass weight  $M_n$  of the macromonomers. In the graph, macrodiols are represented by -■-; macromonomers by ...●...; and thermosets by —▲—.

The tensile properties of poly( $\epsilon$ -caprolactone) thermosets C1 through C7 at room temperature are shown below in Table 13, wherein  $E$  is the elastic modulus (Young's modulus),  $\epsilon_s$  is the elongation and  $\sigma_s$  is the stress at the yield point,  $\sigma_{\max}$  is the maximum stress,  $\epsilon_{\max}$  is the elongation at  $\sigma_{\max}$ ,  $\epsilon_R$  is the elongation at break, and  $\sigma_R$  is the stress at break. Table 14 provided below shows the tensile properties of the same poly( $\epsilon$ -caprolactone) thermosets at 70 °C.

**Table 13: Thermoset Tensile Properties at Room Temperature**

name	E [MPa]	$\epsilon_s$ [%]	$\sigma_s$ [MPa]	$\epsilon_{max}$ [%]	$\sigma_{max}$ [MPa]	$\epsilon_R$ [%]	$\sigma_R$ [MPa]
C1	2.4±0.6	-	-	16.1±2.0	0.4±0.1	16.1±2.3	0.38±0.02
C2	35±3	-	-	20.6±0.3	4.7±0.1	20.6±0.3	4.7±0.1
C3	38±1	48±1	11.2±0.1	180±20	12.1±1.2	190±20	11.7±1.6
C4	58±4	54±1	12.2±0.1	247±4	13.6±1.9	248±13	15.5±2.7
C5	72±1	56±2	15.5±0.2	275±10	15.6±1.7	276±6	15.0±1.0
C6	71±3	43±2	14.2±0.1	296±14	15.5±0.2	305±8	13.8±2.7
C7	71±2	42±5	13.6±0.2	290±30	16.2±0.5	290±30	15.7±0.9

**Table 14: Thermoset Tensile Properties at 70 °C**

name	E [MPa]	$\sigma_{max}$ [MPa]	$\epsilon_R$ [%]
C1	1.84 ± 0.03	0.40 ± 0.08	24 ± 6
C2	2.20 ± 0.12	0.38 ± 0.05	18 ± 2
C3	6.01 ± 0.12	2.05 ± 0.21	43 ± 9
C4	2.30 ± 0.16	0.96 ± 0.01	61 ± 3
C5	1.25 ± 0.08	0.97 ± 0.15	114 ± 13
C6	1.91 ± 0.11	1.18 ± 0.06	105 ± 11
C7	0.70 ± 0.09	0.79 ± 0.10	210 ± 7

## 5 Shape Memory Properties

The thermosets were determined to have the thermomechanical properties indicated in Table 15. The number average molecular weights ( $M_n$ ) is of the macromonomer. The lower limit temperature,  $T_l$ , is 0 °C, and the higher limit temperature,  $T_h$ , is 70 °C. The extension in the temporary shape is 50%.  $R_r(2)$  is the strain recovery rate of the second cycle,  $R_{r,tot}$  is the total strain recovery rate after 5 cycles,  $R_f$  is the average strain fixity rate.

**Table 15: Thermoset Thermomechanical Properties**

name	$M_n$ [g·mol <sup>-1</sup> ]	$R_r(2)$ [%]	$R_{r,tot}$ [%]	$R_f$ [%]
C4	4,500	93.3	93.0	93.9± 0.2
C5	6,500	96.3	94.5	93.9± 0.2
C6	7,000	93.8	92.1	92.5± 0.1
C7	10,000	98.6	96.8	86.3± 0.5

We claim:



1. A biodegradable shape memory polymer composition.
2. The composition of claim 1 comprising:
  - a) at least one hard segment which has a  $T_{trans}$  between -40 and 270 °C,
  - b) at least one soft segment which has a  $T_{trans}$  at least 10 °C lower than that of the hard segment(s), which is linked to at least one hard segment, wherein at least one of the hard or soft segments includes a biodegradable region or at least one of the hard segment(s) is linked to at least one of the soft segment(s) through a biodegradable linkage.
3. The composition of claim 2 wherein the  $T_{trans}$  of the hard segment is in the range of between 30 and 150 °C.
4. The composition of claim 3 wherein the  $T_{trans}$  of the hard segment is in the range of between 30 and 100 °C.
5. The composition of claim 2 wherein the  $T_{trans}$  of the soft segment(s) is at least 20 °C below that of the hard segment(s).
6. The composition of claim 2 wherein at least one of the hard and soft segments is a thermoplastic polymer.
7. The composition of claim 2 wherein the hard segment comprises cyclic moieties.
8. The composition of claim 2 wherein the ratio by weight of the hard and soft segments is between about 5:95 and 95:5.
9. The composition of claim 1 wherein the shape memory polymer is selected from the group consisting of graft polymers, linear polymers, and dendrimer polymers.
10. The composition of claim 1 wherein polymer comprises a biodegradable region selected from the group consisting of polyhydroxy acids, poly(ether ester)s, polyorthoesters, poly(amino acids), synthetic poly(amino acids), polyanhydrides, polycarbonates, poly(hydroxyalkanoate)s, and poly( $\epsilon$ -caprolactone)s.

11. The composition of claim 1 wherein the polymer comprises a biodegradable linkage selected from the group consisting of ester groups, carbonate groups, amide groups, anhydride groups, and orthoester groups.
12. The composition of claim 1 wherein the polymer is completely degradable.
13. The composition of claim 1 comprising:  
a degradable thermoset polymer that comprises a covalently crosslinked crystallizable soft segment having a  $T_m$  between 250 °C and -40 °C.
14. The composition of claim 13 wherein the degradable thermoset polymer comprises a covalently crosslinked crystallizable soft segment having a  $T_m$  between 200 °C and 0 °C.
15. The composition of claim 1 comprising
  - a) at least one first segment which has a  $T_{trans}$  between -40 and 270 °C,
  - b) at least one second segment which is linked to at least one first segment, and which comprises ionic interactions of sufficient strength that the second segment has no melting or glass transition temperature, wherein at least one of the first or second segments includes a biodegradable region or at least one of the first segments is linked to at least one of the second segments through a biodegradable linkage.
16. The composition of claim 15 wherein the ionic interaction comprises polyelectrolyte segments or supramolecular effects based on highly organized hydrogen bonds.
17. The composition of claim 1 wherein the polymer has an inverse temperature effect.
18. The composition of claim 1 wherein the polymer changes shape in response to light.
19. The composition of claim 1 wherein the polymer is a polymer blend.
20. The composition of claim 1 comprising a coating altering the degradation of the shape memory polymer.
21. An article comprising the biodegradable shape memory polymer composition of any of claims 1-20.



22. The article of claim 21 incorporating an agent selected from the group consisting of therapeutic, diagnostic and prophylactic agents.
23. The article of claim 21 wherein the article is implantable and the biodegradable shape memory polymer is biocompatible.
24. The article of claim 23 wherein the shape memory polymer does not contain aromatic groups.
25. The article of claim 21 wherein the article is a medical device selected from the group consisting of stents, catheters, prosthetics, grafts, screws, pins, pumps, and meshes.

1/5

**FIG. 1****FIG. 2**

2/5

P=THERMOPLASTIC MATERIALS



SOFT SEGMENT




HARD SEGMENT

O - JUNCTION UNIT

P0 - SEMICRYSTALLINE HOMOPOLYMERS, SEMICRYSTALLINE COPOLYMERS AND BLENDS THEREOF

P1 - THERMOPLASTIC ELASTOMERS WITH LINEAR CHAINS



P2- THERMOPLASTIC ELASTOMERS WITH SIDE CHAINS OR ANY KIND OF DENDRITIC STRUCTURAL ELEMENTS






FIG. 3

3/5






FIG. 4

4/5

**FIG. 5****FIG. 6**

5/5




FIG. 7




FIG. 8

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 99/03977

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 A61L27/00 A61L29/00 A61L31/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 326 426 A (JAPAN MEDICAL SUPPLY CO., LTD. ) 2 August 1989 see page 2, line 25 - line 31; claims 1,5	1,9-12, 21-25
X	WO 95 34331 A (AO FORSCHUNGSINST ;GOGOLEWSKI SYLWESTER (CH); GANZ RHEINOLD (CH)) 21 December 1995 see page 5, line 19 - line 22; claims 8,10	1,9, 21-25
A	DE 42 26 465 A (GUNZE LTD.) 11 February 1993 see claims 1,3	1,10-12, 19,21-25

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance  
"E" earlier document but published on or after the international filing date  
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)  
"O" document referring to an oral disclosure, use, exhibition or other means  
"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention  
"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone  
"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.  
"&" document member of the same patent family

Date of the actual completion of the international search

8 June 1999

Date of mailing of the international search report

15/06/1999

Name and mailing address of the ISA  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Angiolini, D

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/03977

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 326426 A	02-08-1989	JP 1192367 A	02-08-1989
		JP 2561853 B	11-12-1996
		CA 1307885 A	29-09-1992
		DE 68920055 D	02-02-1995
		DE 68920055 T	11-05-1995
		US 4950258 A	21-08-1990
WO 9534331 A	21-12-1995	NONE	
DE 4226465 A	11-02-1993	JP 5042202 A	23-02-1993
		JP 5309103 A	22-11-1993